



**PRODUCT INFORMATION SHEET**

**43 AM (D)**

<b>CLASSIFICATION</b>	<b>Mortar Air Setting- Dry Type</b>		
<b>PHYSICAL PROPERTIES</b>	Pyrometric Cone Equivalent	Orton Cone	31.5-32
	Approximate Amount of Water for trowelling consistency	Litres/50 kg	25
	Approximate Amount of Water required per 1000 pcs 9" standard brick equivalent thinly trowelled joints	%	170
	Modulus of Rupture After Drying at 110 <sup>0</sup> C	Kg./cm <sup>2</sup>	20
<b>CHEMICAL COMPOSITION</b>	Alumina (Al <sub>2</sub> O <sub>3</sub> )	%	54.0
	Silica (SiO <sub>2</sub> )	%	40.0
	APPROX. (%) Iron Oxide (Fe <sub>2</sub> O <sub>3</sub> )	%	1.6

The data cannot be used for specification and guarantee purpose – reasonable variances in data can be expected. Product data is update periodically to reflect product / raw material / process / testing changes. Please contact BST's representative for the most updated data.

**We are refractory solutions**