



PRODUCT INFORMATION SHEET

70 AM (D)

CLASSIFICATION	Mortar Air Setting- Dry Type		
PHYSICAL PROPERTIES	Pyrometric Cone Equivalent	Orton Cone	36-37
	Approximate Amount of Water for trowelling consistency	Litres/50 kg	23
	Approximate Amount of Water required per 1000 pcs 9" standard brick equivalent thinly trowelled joints	%	210
	Modulus of Rupture After Drying at 110 ⁰ C	Kg./cm ²	25
CHEMICAL COMPOSITION	Alumina (Al ₂ O ₃)	%	68.5
	Silica (SiO ₂)	%	27.5
	APPROX. (%) Iron Oxide (Fe ₂ O ₃)	%	1.5

The data cannot be used for specification and guarantee purpose – reasonable variances in data can be expected. Product data is update periodically to reflect product / raw material / process / testing changes. Please contact BST's representative for the most updated data.

We are refractory solutions